

## THEVA PRO-LINE HTS WIRE

Dezember 2017

### General Properties



## General remarks on HTS wire technology

High-temperature superconductors (HTS), especially compounds of the family  $\text{REBa}_2\text{Cu}_3\text{O}_{7-\delta}$  (REBCO; RE = rare earth element, e.g. Yttrium Y, Dysprosium Dy, or Gadolinium Gd) are powerful for industrial applications. Compared to low-temperature superconductors, cooling with liquid helium is not necessary and very high current densities above  $10^{10} \text{ A/m}^2$  or  $10,000 \text{ A/mm}^2$  can be realised with this material. For technical applications, the following basic properties and remarks are important:

- REBCO is a ceramic compound. To overcome the brittleness of the material, thin films on flexible metallic substrates are used. As the bending strain in a thin film on a thin metal substrate is small, a flexible wire can be realised.
- In superconductors like REBCO irregularities of the crystalline structure in the nanometer range result in a disturbance of the superconductivity.
- Any superconductor has a certain limit of current that it can carry. If this current is exceeded, a resistance develops which leads to fast heating. This can destroy the thin superconducting layer easily if the current is not switched off fast. In order to achieve a more robust behaviour, an electrical stabilization like an additional copper layer is used typically. The type and thickness of this layer is determined by the specific application requirements. The copper also serves as mechanical and chemical protection.



## THEVA Pro-Line wires

The metal substrate for THEVA Pro-Line (TPL) wires is the Nickel alloy NiMo16Cr15W (also known as Hastelloy C-276<sup>1</sup>, 2.4819, or N10276). The rolled strip material has excellent mechanical properties which guarantee a high quality HTS wire.




Fig. 1: Sketch of the ISD process.

To achieve the necessary texture a buffer layer of magnesium oxide (MgO) is deposited onto the substrate prior to the  $\text{GdBa}_2\text{Cu}_3\text{O}_{7.5}$ . Texturing of this layer is achieved by THEVA's proprietary inclined substrate deposition (ISD) process<sup>2</sup>. During the deposition of MgO, the substrate is inclined with respect to the source as shown in **Fig. 1** resulting in a MgO layer with a roof tile surface structure and a tilt of the main crystallographic axes (indicated as [001] in **Fig. 1**) as well as a pronounced biaxial texture (**Fig. 2**).

To facilitate epitaxial growth of the superconductor a second thin MgO layer (cap layer) is evaporated onto the ISD layer. The HTS layer is then deposited directly onto this second MgO layer. For

Pro-Line wires pure  $\text{GdBa}_2\text{Cu}_3\text{O}_{7.5}$  is used which has a critical temperature of 92 K. All depositions are performed in vacuum (PVD) using e-beam evaporation.




Fig. 2: scanning electron microscope (SEM) cross section image (left) and SEM surface image of the ISD-MgO layer (right) (both at a magnification of 50k).

Due to the epitaxial growth, the orientation of the MgO is adopted by the HTS film including the tilt. Therefore, the c-axis of the HTS film is tilted by approximately 30° with respect to the substrate normal. The tilt is always perpendicular to the tape direction (**see Fig. 2**). As the performance of HTS is related to the crystallographic orientation, the tilt leads to a distinct angular dependence of the magnetic field performance (see below).

<sup>1</sup> Hastelloy C-276 is a trademark of Haynes International

<sup>2</sup> EP0909340, US6265353, US6638598

# THEVA Pro-Line HTS wire – general properties

On top of the HTS layer, a thin silver layer is deposited as electrical contact and chemical protection layer. The final basic layer structure is shown in **Fig. 3**. This type of wire is the **THEVA Pro-Line (TPL) 1000-series**. For example, it can be used directly for fault current limiter applications.




Fig. 3: Architecture of the TPL1000-series. Thicknesses of the layers are typical values only.

For applications that would need better electrical and mechanical stabilization, the TPL2000- and 4000-series are available.

In the case of the **TPL2000-series**, a copper foil, with a thickness of 50 μm or 100 μm, is laminated onto the silver coating on the HTS side (**see Fig. 4**). The thick copper foil ensures a high electrical stability of the wire as well as a robust mechanical protection.

For the **TPL4000-series**, a copper surround layer is deposited around the tape using an electroplating process (**see Fig. 5**). Here the thickness of the copper layer is 10 to 20 μm. This type has high engineering current densities useful for e.g. high-performance magnets.

Pro-Line HTS wires are available with a width of 12 mm down to 3 mm. Detailed information on deliverable width values as well as different copper or silver thickness are available upon request.




Fig. 4: Architecture of the TPL2000-series




Fig. 5: Architecture of the TPL4000-series

## Electrical Properties

In general, the maximum current depends on the temperature, external magnetic field and its angle of impingement. In **Fig. 6** the typical temperature dependence of the  $I_c$ -value with no external magnetic field is plotted.

The dependence of  $I_c$  on temperature, magnetic field, and its angle relative to the superconducting layer is usually expressed by the so-called lift factor which is the ratio of  $I_c$  under this condition ( $T$ ,  $B$  and  $B$ -field orientation) and the  $I_c$  at 77 K and selffield (s.f.).

If an external magnetic field is applied to the HTS layer, best performance is achieved when the magnetic flux lines are aligned parallel to the

REBCO ab-planes due to the so called intrinsic pinning effect. Deviations of the alignment cause a drop of the critical current  $I_c$  as shown in the graph of the lift factor as a function of the angle (maximum Lorenz force condition) in **Fig. 7**.

For THEVA Pro-Line wire the peaks are observed at  $\sim 120^\circ$  (or  $300^\circ$ ,  $0^\circ$  is defined as  $B$  perpendicular to the surface) due to the tilted growth of the superconductor as explained above. This means that  $B$  is parallel to the ab-planes of the superconductor ( $B \parallel ab$ ). The tilt direction of the crystallographic  $c$ -axis of THEVA Pro-Line tape is marked on the back side (see below).




Fig. 6: Typical critical current  $I_c$  of a TPL2100 wire as a function of the temperature  $T$ . Boiling temperatures at 1 bar of various cooling agents are also marked.

# THEVA Pro-Line HTS wire – general properties




Fig. 7: Lift factor as a function of the direction of the magnetic field (77 K, 1 T)

A similar angular dependence is found at all temperatures and fields but the shape varies depending on the specific conditions as can be seen in **Fig. 8** for intermediate temperatures and 3 T.

For many applications the direction of the magnetic field is not constant. Therefore, it is useful to know the lift factor under worst case conditions, i.e. at the angle where the  $I_c$  is minimal.

This is the case at about 30° where the magnetic field is parallel to the c-axis of the superconductor. The lift factor under this condition is shown in **Fig. 9**.

Detailed data of the lift factor for THEVA Pro-Line wire for temperatures ranging from 77 K down to 4.2 K and for magnetic fields up to 8 T is available upon request.




Fig. 8: Lift factor as a function of the direction of the magnetic field (25 – 40 K, 3 T)




Fig. 9: Lift factor for B // c at various temperatures

# THEVA Pro-Line HTS wire – general properties

## Marking

All THEVA Pro-Line wires are marked on the substrate side (back side) as shown in **Fig. 10**. The marking consists of a symbol and a number. The number indicates the position in m which correlates directly and precisely to the available  $I_c$  measurement data whereas the symbol indicates the c-axis orientation.

As shown in **Fig. 11**, the triangle has to be taken as a projection to the HTS side (front side) of the tape. The tip (first tip) of the leg perpendicular to tape direction indicates the c-axis orientation of the HTS layer whereas the tip of the other leg (second tip) is pointing into the direction of the tape's end (increasing meter values printed on the tape's back side).




Fig. 10: Photograph of the substrate side (back side) of a TPL1100 tape. The length position (24.6 m) and the triangle (marking for the c-axis orientation) are visible.




Fig. 11: Sketch of the triangle printed to the back side of a TPL tape and the corresponding c-axis tilt direction.

# THEVA

THEVA Dünnschichttechnik GmbH

Rote-Kreuz-Straße 8 • 85737 Ismaning • Germany • [info@theva.com](mailto:info@theva.com) • [www.theva.com](http://www.theva.com)

### Disclaimer

The information contained in this brochure is provided as is and without any warranties of any kind, whether expressed or implied, including but not limited to, implied warranties of satisfactory quality, fitness for a particular purpose and/or correctness. The information of this brochure is for general information purpose only and does not constitute advice.

The author reserves the right not to be responsible for the content, topicality, correctness, completeness, details, specifications or quality of the information provided.

No liability whatsoever is accepted for the content and information provided.

All offers are not-binding and without obligation. Parts of the pages or the complete publication including all offers and information might be extended, changed or partly or completely deleted by the author without separate announcement.

The content and works provided in this brochure are governed by the copyright laws of Germany. Any duplication, processing, distribution or other use of objects such as images, diagrams, sounds or texts or any form of commercialization of such material beyond the scope of the copyright law shall require the prior written consent of the respective author or creator.